



Received on 18 July, 2017; received in revised form, 10 October, 2017; accepted, 17 November, 2017; published 01 April, 2018

## SYNTHESIS OF NANOSTRUCTURED MAGNESIUM OXIDE BY SOL GEL METHOD AND ITS CHARACTERIZATION

Mamta Sharma, Dimple Gandhi and Minakshi Sharma\*

Department of Zoology, Maharshi Dayanand University, Rohtak - 124001, Haryana, India.

### Keywords:

Metal, MgO,  
Nanoparticle, Catalyst, Technique

### Correspondence to Author:

**Minakshi Sharma,**

Professor,  
Department of Zoology,  
Maharshi Dayanand University,  
Rohtak - 124001, Haryana, India.


**Email:** sminakshi.2007@rediffmail.com

**ABSTRACT:** Metals are able to form a large number of oxides. These metal oxides play an important role in many areas of chemistry, physics and material science. An important metal oxide known as magnesium oxide (MgO) having good reactivity is widely used in producing electronics, catalyst, ceramics, oil, paint *etc.* Magnesium oxide nanoparticle is non-toxic and need a small amount, so it is suitable for the development of flame-retardant fiber additives. In addition, nano magnesium oxide added in fuel can inhibit corrosion. Spherical shaped Magnesium oxide nanoparticles were successfully synthesized by sol-gel technique at room temperature using magnesium nitrate and sodium hydroxide as a precursor. The morphological investigation of MgO nanoparticles was done by various analytical techniques. X-ray Diffraction (XRD) indicates the crystallinity and crystal size of MgO nanoparticle. Transmission electron microscopy (TEM) tells about the particle size and morphology. Fourier transform infrared microscopy was used to get the infrared spectrum of the sample indicating powdered composition of the sample. UV-Visible spectroscopy was used to know the optical properties of the sample. Result confirms that brucite phase magnesium hydroxide gets converted to magnesium oxide periclase phase at room temperature.

**INTRODUCTION:** In recent year, nanoparticles have attracted a great attention because of their unique physical and chemical properties such as higher damping property, mechanical stability and high strength with good thermal conductivity<sup>1</sup>. Metal oxide nanomaterials having high surface area have attracted considerable interest for scientific research due to their applications in the field of optical electronics, sensing devices and nano electronics<sup>2</sup>.

The growing importance of high surface reactivity, chemical stability and thermal stability of MgO makes it a promising material for the application in sensor, catalysis, paint, additives *etc.* Researchers have focused more on the synthesis of both nanoparticles and nano composite of MgO due to their application in advanced technologies<sup>3</sup>.

MgO is an important inorganic oxide which has been widely used in many fields<sup>4</sup>. It is a semiconductor which crystallizes in the rock salt/sodium chloride type cubic structure<sup>5</sup>. Many synthesis processes such as sol-gel, hydrothermal, flame spray pyrolysis, combustion, aqueous wet chemical, surfactant and chemical gas phase deposition methods have been studied for the synthesis of MgO nanoparticles<sup>6</sup>. Many physicochemical techniques are also there to

<p><b>QUICK RESPONSE CODE</b></p> 	<p><b>DOI:</b> 10.13040/IJPSR.0975-8232.9(4).1576-81</p> <hr/> <p>Article can be accessed online on: <a href="http://www.ijpsr.com">www.ijpsr.com</a></p>
<p><b>DOI link:</b> <a href="http://dx.doi.org/10.13040/IJPSR.0975-8232.9(4).1576-81">http://dx.doi.org/10.13040/IJPSR.0975-8232.9(4).1576-81</a></p>	

construct nanosized MgO particles<sup>7</sup>. The size and morphology of oxide particle can be controlled by many parameters such as pH, ionic strength, temperature of precipitation and different calcinations temperature<sup>8</sup>. Over the past decades, various precursors were used in the synthesis of nanosized MgO resulting in multiple morphologies. Precursors that can be obtained from the synthesis methods take many forms such as magnesium hydroxide<sup>9</sup>, magnesium carbonate<sup>10</sup> and basic magnesium carbonate<sup>11</sup>.


Various fabrication techniques are also employed to synthesize MgO nanoparticles having their own advantages and disadvantages<sup>12</sup>. Spherical shaped magnesium oxide nanoparticles were synthesized successfully by sol-gel method using magnesium nitrate and sodium hydroxide<sup>13</sup>. A sol-gel method is an important technique for the formation of magnesium hydroxide followed by annealing at room temperature to form MgO. After synthesis of MgO nanoparticles, the study of structural, morphological and optical properties was carried out by using techniques such as XRD, FTIR, TEM and UV visible spectroscopy. The present work was aimed to synthesis of MgO nanoparticles chemically and their characterization at room temperature.

#### MATERIALS AND METHODS:

**Materials:** The chemicals required for the formation of magnesium oxide nanoparticles are magnesium nitrate ( $\text{MgNO}_3 \cdot 6\text{H}_2\text{O}$ ), deionized water, sodium hydroxide (NaOH), methanol.

**Apparatus:** Digital pH meter, magnetic stirrer, beaker, funnel, stirrer, filter paper, test tube, dropper. UV-visible spectrophotometer, FTIR machine, Transmission electron microscope (TEM), X-ray diffractometer (XRD).

**Preparation of MgO Nanoparticles:** Magnesium oxide nanoparticles were prepared by sol-gel technique<sup>13</sup>. These were synthesized using magnesium nitrate ( $\text{MgNO}_3 \cdot 6\text{H}_2\text{O}$ ) as a precursor. Firstly, 0.2 M magnesium nitrate was mixed in 100 ml of de-ionized water. Thereafter, 0.5M sodium hydroxide solution was added to the magnesium nitrate solution (which was prepared earlier) drop wise with continuous stirring (30min).



Appearance of white precipitate in the beaker shows the formation of magnesium hydroxide. The pH of the solutions was 12.5, as measured by the digital pH meter. Filtered precipitate washed with methanol is dried at room temperature. Washing with methanol removes ionic impurities. The dried white powder was annealed in air for one to two hours to obtain MgO powder (Fig. 1).




FIG. 1: MAGNESIUM OXIDE PRECIPITATES




FIG. 2: FLOW CHART OF PREPERATION

**Characterization of MgO Nanoparticles:** The characterization of synthesized samples was done by following analytical techniques, such as FTIR, UV-visible, TEM, and XRD.

**UV-visible Spectroscopy:** UV-visible spectroscopy is used to discuss the optical properties of a sample. A monochromatic light is passed through the sample and the amount of light being absorbed by the sample is measured. At different wavelength, absorption of light by sample varies. It follows Beer-Lamberts law which states that absorption is directly proportional to the incident radiation and concentration of solution.

**Fourier Transform Infrared Spectroscopy (FTIR):** It is a technique used to obtain an infrared spectrum of absorption of a sample which may be in any form (solid, liquid or gas). The goal of FTIR is to measure how well a sample absorbs light at different wavelength. FTIR measurement of magnesium oxide nanoparticles shows different peaks at different levels which corresponds to particular functional group and stretch present in it.


**X-ray Diffraction:** XRD is a conventional technique used for phase identification of a sample possessing crystallinity. It also provides information on unit cell dimensions. The resulting material is ground, homogenized, and bulk composition is determined. It is based on Bragg's law which relates the wavelength of radiation with the

diffraction angle and lattice spacing in crystalline sample.

**Transmission Electron Microscope:** It is used to determine the size of a nanoparticle. TEM is a microscopic technique in which a beam of light is passed through an ultra thin specimen. The interaction of electrons with the specimen results in formation of image which is then magnified and focused onto an imaging device, such as fluorescent screen or CCD camera. TEM analyze the quality, shape, size and density of nanoparticle at high resolution. Nanoparticle can have different shapes, but NPs of magnesium oxide have spherical shape.

## RESULTS AND DISCUSSION:


**Fourier Transform Infrared Spectroscopy (FTIR) Analysis:** The composition of the sample was analyzed by the FTIR measurement. The MgO powder was mixed with potassium bromide and a pellet is made which was used for infrared spectroscopic measurement at room temperature: The absorption band at  $1638.01\text{ cm}^{-1}$  indicates the bending mode of vibration in water ( $\text{H}_2\text{O}$ ) and the broad absorption band at  $3427.50\text{ cm}^{-1}$  indicates the stretching mode of vibration in hydroxyl (OH) group. The peak at  $1051.94\text{ cm}^{-1}$  is due to adsorption of  $\text{CO}_2$ , whereas peaks at  $827.78\text{ cm}^{-1}$  attributes to different Mg-O-Mg vibration modes of MgO (**Fig. 3**). FTIR was done at Pharmaceutical Department, MDU Rohtak.



**FIG. 3: FTIR SPECTRA OF MgO NANOPARTICLES**

**UV-visible Spectral Analysis:** The optical properties of the MgO NPs were studied by means of the UV-visible absorption spectra in wavelength range of 200 - 1000 nm. The maximum absorption band of MgO NPs was found at 230.3 nm (**Fig. 4**).


It has been found that firstly the absorbance decreases with an increase in wavelength. UV-Visible spectroscopy was done at Zoology Department, MDU Rohtak.



**FIG. 4: UV SPECTRA OF MgO NANOPARTICLES**

**X-ray Diffraction (XRD) Analysis:** The crystal structure of MgO nanoparticle was determined by XRD analysis. From the peak width and intensity the small particle size and better crystallinity can be easily seen. The peaks in XRD pattern of the prepared MgO sample is observed at  $2\theta$  -19.02,

29.70, 38.31, 51.11 and 59.98 (**Fig. 5**). XRD was done at Chemistry Department, MDU Rohtak. Average particle size of the nanoparticle was determined using Debye - Scherrer equation and it was found to be 22 nm.



**FIG. 5: XRD PATTERN OF MgO NANOPARTICLES**

**Transmission Electron Microscopy (TEM) Analysis:** TEM is a technique used as the principle characterization for the direct observation of nanoparticles generated. The size of MgO nanoparticles was found 0.2  $\mu\text{m}$  (**Fig. 6**) and 100 nm (**Fig. 7**).

TEM image of MgO sample, shows that MgO nano crystallite exhibit spherical shape and very homogenous crystal structure without any observable pores. TEM was done at AIIMS (All India Institute for Medical Science), New Delhi.






FIG. 6: TEM IMAGE OF MGO NANOPARTICLES (0.2 $\mu$ M)




FIG. 7: TEM IMAGE OF MGO NANOPARTICLES (100 nm)

**CONCLUSION:** In the present work, MgO was successfully synthesized by liquid phase method *i.e.* sol-gel technique as this technique is simple, fast and effective. Magnesium oxide nanoparticles were chemically synthesized using magnesium nitrate as a precursor. Shape, size and other characteristics of nanoparticles are characterized by various analytical techniques. FTIR measures infrared intensity *v/s* wavelength of light. It determine the nature of functional groups and structural features of biological extracts with nanoparticles. It shows different peaks corresponding to different functional groups.

XRD is a conventional technique which is used to understand crystallographic structure and morphology. From UV-visible spectroscopy, optical properties of MgO nanoparticles were known. TEM is considered as the best tool in confirming the shape and size of nanoparticles. Magnesium oxide nanoparticles have various applications in different fields such as oil, paints,

ceramics, medicine, drugs *etc.* It is used as an additive in heavy fuel oils reflecting and anti-reflecting coatings in optics.

**ACKNOWLEDGEMENT:** Nil

**CONFLICT OF INTEREST:** The authors declare no conflict of interest.

#### REFERENCES:

1. Gray JE and Luan B: Protective coatings on magnesium and its alloys- a critical review. *Journal of Alloys and Compounds* 2002; 336: 88-113.
2. Jintakosol T and Singjai P: Effect of annealing treatment on luminescence property of MgO nanowires. *Current Applied Physics* 2009; 9: 1288-1292.
3. Nga NK, Hong PT, Lam TD and Huy TQ: A facile synthesis of nanostructured magnesium oxide particles for enhanced adsorption performance in reactive blue19 removal. *Journal of Colloidal Interface* 2013; 398: 210-6.
4. Sawai J, Kojima H, Igarashi H, Hasimoto A, Shoji S, Sawaki T, Hakoda A, Kawada E, Kokugan T and Shimizu M: Antibacterial characteristics of magnesium oxide powder. *World Journal of Microbiology and Biotechnology* 2000; 16:187-194.

5. Spoto G, Zecchina A, Bordiga S, Ricchiardi G, Martra G, Lefanti G and Petrin G: Cu(I)-ZSM-5 zeolites prepared by reaction of H-ZSM-5 with gaseous CuCl: Spectroscopic characterization and reactivity towards carbon monoxide and nitric oxide. *Applied Catalysis B* 1994; 3: 151-172.
6. Kumar A and Kumar J: On the synthesis and optical absorption studies of nanosize magnesium oxide powder. *J. Phys. Chem. Solids* 2008; 69: 2764-2772
7. Nga NK, Hong PT, Lam TD and Huy TQ: Surfactant-assisted size control of hydroxyapatite nanorods for bone tissue engineering. *Journal of Colloid Interface Science* 2013; 398: 210 -216.
8. Laska M, Valtyni J and Fellner P: Influence of pH on the crystal size distribution of Mg(OH)<sub>2</sub> prepared by the hydration of MgO. *Crystal Research* 1993; 28: 931.
9. Kamarulzaman N and Yoozbashizadeh: Mechanically activated synthesis of single crystalline MgO nanostructures. *Journal of Alloys Compounds* 2010; 506: 715-720.
10. Kumari L, Li WZ, Vannoy CH, Leblanc RM and Wang DZ: Synthesis, characterization and optical properties of Mg(OH)<sub>2</sub> micro-/nanostructure and its conversion to MgO. *Ceramic International* 2009; 35: 3355-3364
11. Mastuli MS, Kamarulzaman N, Nawawi MA, Mahat AM, Rusdi R and Kamarudin N: Growth mechanisms of MgO nanocrystals *via* a sol-gel synthesis using different complexing agents. *Nanoscale Research Letter* 2014; 9: 134.
12. Shukla SK, Parashar GK, Mishra AP, Misra P, Yadav BC, Shukla RK, Bali LM and Dubey GC: Nano-like magnesium oxide films and its significance in optical fiber humidity sensor. *Sensors and Actuators B: Chemical* 2004; 98: 5-11.
13. Rizwan W, Absari S, Dar M, Kim Y and Shin H: Synthesis of magnesium oxide nanoparticles by sol-gel process. *Material Science Forum* 2007; 1: 558-559.

**How to cite this article:**

Sharma M, Gandhi D and Sharma M: Synthesis of nanostructured magnesium oxide by sol gel method and its characterization. *Int J Pharm Sci Res* 2018; 9(4): 1576-81. doi: 10.13040/IJPSR.0975-8232.9(4).1576-81.

All © 2013 are reserved by International Journal of Pharmaceutical Sciences and Research. This Journal licensed under a Creative Commons Attribution-NonCommercial-ShareAlike 3.0 Unported License.

This article can be downloaded to **ANDROID OS** based mobile. Scan QR Code using Code/Bar Scanner from your mobile. (Scanners are available on Google Playstore)